

# TECHNICAL DATA

## REGUPOL SONUSFIT m517 40mm underlay



Properties	Standard	Result
Material		PUR foam bound with polyurethane
Thickness		40mm
Dimensions		Sheets: 2m x 1m
Weight	+/- 20 % DIN EN ISO 845	10.4 kg/m <sup>2</sup>
Tensile Strength	following DIN EN ISO 1798	> 150 kPa
Elongation at Break	following DIN EN ISO 1798	> 40 %
Stress at 40% compression	DIN EN ISO 3386-1	190 kPa
Rebound resilience	DIN EN ISO 8307	29 %
Temperature resistance		- 40°C up to 115°C
Material Tolerance		Length: ±5 mm Width: ± 5 mm Thickness: ±1.6 mm

Should any questions arise that need clarification, contact your sales representative at our company directly or write to us using the contact form on our website [www.regupol.com.au](http://www.regupol.com.au)

Please request a product sample from your **REGUPOL** team before making a decision. The **REGUPOL everroll** rubber flooring is made from recycled materials, variations in the shading, EPDM and colour chip dispersion is normal.

We reserve the right to make alterations to the technical data. All information is subject to fluctuation tolerances of ± 10 %. To verify the accuracy of the contents, please refer to the information on our website [www.regupol.com.au](http://www.regupol.com.au)